

PRODUCT DESCRIPTION

Res-Tek PUR-Guard™ Cove base (CB) is a low odor, 3 component, vertical grade, phthalate free, trowel-applied cementitious urethane mortar engineered for monolithic integration with industrial floor systems. It establishes a continuous, non-porous floor-to-wall transition, resistant to thermal cycling, aggressive chemical exposure, and mechanical impact loading in demanding industrial and commercial environments. PUR-Guard CB can be used for detailing, vertical work, and cove base.

TYPICAL USES

- Food and Beverage
- Breweries/Wineries
- Manufacturing facilities
- Warehouse traffic areas
- Aircraft hangars
- Laboratories
- Dining areas
- Restrooms
- Commercial kitchens
- Dairies

Component	Part A	Part B	Part C	Pigment
Shelf Life	12 months	12 months	9 months	12 months

PROPERTIES

- Meets FDA/USDA requirements
- Antimicrobial properties
- Withstands thermal shock up to 220°F
- High tolerance of moisture vapor transmission
- High abrasion and impact resistance
- Installs on green (10-day old) concrete
- Chemical resistant
- Matching seamless cove base for wall protection
- Designed specifically to withstand heavy impact and traffic
- Minimal maintenance costs

STORAGE CONDITIONS

Store material in a cool and dry place out of direct sunlight. Do not store near open flame or ignition source. Read and understand all product labels and SDS sheets prior to use.

APPLICATION CONDITIONS	
Application Temperature	60° to 80°F
Substrate Temperature	≤ 5°F above dew point
Relative Humidity	25% - 80%


PHYSICAL CHARACTERISTICS

Compressive Strength ASTM C579 (psi)	8,200	Shore D Hardness ASTM D2240	86
Tensile Strength ASTM C307 (psi)	980	VOC (g/L):	0 g/L
Impact Resistance	No visible damage at minimum 160 in. -lb.	Adhesion ASTM D7234	Exceeds the tensile/cohesive strength of concrete


For the most current Product Data and Application information, consult your Res-Tek representative. The information and recommendations in this Product Data Sheet are based on tests conducted by or on behalf of Res-Tek, in a controlled environment, and reflect current information as of the publication date. This information is subject to change.




COLOR OPTIONS - PUR-Guard systems are available in several standard color options.



P-21 (Gray)




P-22 (Dark Gray)



P-23 (Black)



P-24 (Red)



P-25 (Green)



P-27 (Beige)



P-28 (Chocolate)

STANDARD PACKAGING

COMPONENT	ITEM NAME	FILL
Part A	PUR-Part-A-0.25GAL	0.25 gal
	PUR-Part-A-0.5GAL	0.5 gal
	PUR-Part-A-1GAL	1 gal
	PUR-Part-A-5GAL	5 gal
	PUR-Part-A-50GAL	50 gal
	PUR-Part-A-250GAL	250 gal
Part B	PUR-Part-B-0.25GAL	0.25 gal
	PUR-Part-B-0.5GAL	0.5 gal
	PUR-Part-B-1GAL	1 gal
	PUR-Part-B-5GAL	5 gal
	PUR-Part-B-50GAL	50 gal
	PUR-Part-B-250GAL	250 gal
Part C	PUR-Part-C-CB	26 lb. bag

	THICKNESS	THEORETICAL COVERAGE
CB MIX YIELDS	4"	35 LF
	8"	23 LF

CURE TIME @ 70°F RH 50%

	RECOAT/FOOT TRAFFIC	FULL CURE
CB	6-8 hours	24 hours

MOISTURE MITIGATION

For moisture mitigation above PUR-Guard limits, Calcium Chloride (ASTM F-1869) 20 lb/1000 sq.ft./24 hrs, or 99% RH using in-situ RH probe (ASTM F-2170), additional products are required. If waterproofing is required please consult your Res-Tek representative for more information.

PRIMING

Priming is required prior to use of the PUR-Guard CB. The primed area should be allowed to dry tack free before proceeding with the body coat application. ~~We recommend the PUR-Guard TC~~ however if your installation requires an alternate application contact your Res-Tek sales representative.

MIXING & APPLICATION

- Mix Only Full Kits, Do Not Split.
- Mix in ~~5 gallon plastic~~ pail using a low speed drill equipped with a spiral mixing blade.
- Refer to product labeling or mixing chart for exact instructions.
- Add Part A to mixing bucket, add pigment pack and mix until blended, add Part B and mix for 15 - 30 seconds only.
- With mixer running, immediately add approximately one quarter of the appropriate filler.
- Gradually add remainder of filler and mix until blended and lump free.
- Mixing should take no longer than 2-3 minutes.
- Apply material to floor immediately after mixing.
- Spread to specified thickness using a ~~cam, gauge, or 1/2" v notched squeegee.~~
- ~~Once material is placed, using a 3/8" nap roller back roll to smooth imperfections.~~
- ~~Use of a loop roller is necessary to de-aerate and level to desired thickness.~~
- ~~Broadcast immediately with Res-Tek approved aggregate of choice.~~

Please refer to the Application Guide for detailed instructions.

TOPCOAT

After thorough sweeping and vacuuming, apply PUR-Guard TC topcoat at 130 - 135 sq.ft. per mix.

WARRANTY

Res-Tek Inc. warrants that materials shipped to buyers are free of any defects in material or workmanship according to Res-Tek's published data if used in accordance with Res-Tek's specified application procedure. Res-Tek Inc. shall not be responsible for any claim resulting from failure to utilize product in the manner in which it was intended, and in accordance with Res-Tek's application guidelines. Res-Tek Inc. has no responsibility for application and processing of products.

- This product data sheet was prepared as a general guide only. Please contact your local Res-Tek Representative or our Technical Service department for assistance prior to any application.