

LUXE PP ZERO - NO ODOR POLYASPARTIC

DESCRIPTION

LUXE PP Zero is a two-component, slow cure, no-odor, polyaspartic topcoat designed as a decorative and durable coating for commercial and residential flooring. Formulated with aliphatic chemistry, **LUXE PP Zero** is color stable and will resist UV exposure without color change, as seen with other coating systems such as epoxies. This high-performance coating has a 1 : 1 mix ratio, an extended application window, and little to no effect of humidity on working time.

ADVANTAGES

- Extended working time
- Virtually no odor formulation
- Application tolerant to moisture
- UV resistance, non-yellowing
- High gloss
- Abrasion & impact resistant
- Chemical resistance
- Resists hot tire marking transfer

RECOMMENDED USES

- Concrete basecoat and/or topcoat
- Outdoor applications; UV-stable formulation
- Indoor applications; no odor
- Logos with inlays
- Aircraft hangar floors
- Maintenance facilities
- Industrial shop floors
- Car washes or wash bays

PACKAGING	2 US ga. Kit 10 US ga. Kit	
RECOMMENDED THICKNESS	As Topcoat	Solid Color - 6 mils WFT (266 sq.ft. /ga.) Vinyl Chip - 12 mils WFT (140 sq.ft. /ga.)
SHELF LIFE	12 months in original unopened factory sealed containers. Keep away from cold, heat or moisture. Keep out of direct sunlight and away from fire hazards.	
MIX RATIO, BY VOLUME	1A : 1B	
POT LIFE 1 kg MASS	15 mins @ 77°F (25°C)	
WORKING TIME	90 mins	

Changes in ambient temperature will change working time, increased temperatures will reduce working time, decreased temperatures will extend working time.

SURFACE PREPARATION

- Concrete substrates should be cured for a minimum of 30 days and have a min. compressive strength of 3,000 psi.
- Achieving optimal adhesion requires a clean, mechanically prepared substrate. Surfaces must be clean, sound and properly prepared.
- Substrate must have minimum Concrete Surface Profile (CSP) of 3-4.
- Do not apply to wet or damp substrates.
- Test for concrete moisture before application (see Concrete Moisture.)
- Remove all surface dust just prior to application. Protect prepared surface against contamination.

CURE TIMES			
TACK-FREE		4 hours	
RECOAT		Within 24 hours ²	
FOOT TRAFFIC		6 hours	
HEAVY WHEELED TRAFFIC		48 hours	
FULL CURE		4 - 7 days	
TABER ABRASION D4060 (MG LOSS, 1000G, 1000CYCLES)		78.7 mg	
HARDNESS, SHORE D, ASTM D2240		70	
VISCOSITY @ 77°F (25°C)	PART A	PART B	MIXED
	300 - 800 cP	100 - 200 cP	100 - 500 cP
GLOSS, ASTM D523		90+ GU	

²If recoat time window is exceeded, surface must be mechanically prepared before subsequent coats.

**Thinning is not normally required for this product and not recommended.

CONCRETE MOISTURE

- Note although moisture testing is critical it is not a guarantee against future moisture related problems. This is especially true if there is no vapor barrier or the vapor barrier is not functioning properly and or you suspect there is concrete contamination from oils, chemical spills or excessive salts.
- A functioning vapor barrier is required.
- Perform a water droplet test in multiple places to make sure the slab is porous. (Per ASTM 3191).
- Open the pore structure in any nonporous areas and retest before installing.

MIXING

- Precondition all components for 24 hours to ambient temperatures.
- In clean mixing pail, mix entire unit, A & B. Units are premeasured for correct ratio, do not break down units, product performance will be effected.
- Mechanically mix only, do not mix by hand. Do not mix more material than can be distributed and applied in the working time window. Using a Jiffy/Jiffler, or similar type mixing attachment, slowly mix the components being careful not to introduce excessive air.
- Mix for 3 minutes. Ensure all material is scraped by side wall and bottom of mixing container. Apply material to floor immediately after mixing. Delay in distributing product will result in exothermic heat buildup in container.

APPLICATION

The recommended application method is the use of non-marking rubber squeegee and roller application. Notched squeegees of the appropriate notch depth may be used for thicker applications.

18-inch rollers are recommended on larger area floors to reduce lap marks. Roller should have solvent-resistant phenolic core, high quality non-shedding fiber covers. Use 1/4-inch to 3/8-inch nap, depending on final finish and thickness desired. Quality brushes or wall-edgers may be used for cutting in margins.

Distribute material evenly with non-marking (gray EPDM type, or similar) rubber flat squeegee. Apply even film at desired thickness. Roll material in two directions to achieve uniform film. Finish roll in one direction, typically at right angles to primary sight-line when entering room.

- Avoid puddles of material
- Do not apply above recommended thickness

CLEANING

Clean all tools and materials with the cleaner/thinner for polyaspartics. Wash hands and skin carefully with warm soapy water. Once product has hardened, it may only be removed through mechanical means.

LIMITATIONS

Prior to application, measure, and confirm the ambient temperature and humidity conditions of air and substrate.

- Measure and confirm temperature of material. Precondition material for 24 hours prior to mixing.
- Do not allow material to freeze. Frozen material cannot be recovered and must be disposed of.
- Minimum/Maximum substrate temperature at application: 45°F (7.2°C) / 85°F (30°C).
- Maximum relative humidity during application and curing: 80%.
- Substrate must be 5°F (3°C) above dew point. Ensure conditions will not change during application and curing.
- Observe concrete moisture limitations stated in Concrete Moisture section.
- On porous, non-concrete substrates, ensure that there will be no moisture penetration on positive side.
- Protect from moisture and condensation for 24 hours after application.
- Do not apply to substrates exhibiting or tested positive for alkali silica reaction (ASR).
- Do not use propane or kerosene fueled heaters. Permanent discoloration of coating may occur.
- For professional use only by experienced personnel.
- **KEEP CONTAINER TIGHTLY CLOSED**
- **KEEP OUT OF REACH OF CHILDREN**
- **NOT FOR INTERNAL CONSUMPTION**

Prior to use of any product manufactured by APN Specialty Coatings, its subsidiaries or affiliates, the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at <https://purepoxy.com/> or by calling **920-231-0850**.

HEATH & SAFETY

Obtain and wear all required personal protection equipment (PPE.) In case of skin contact, wash with water and soap. In case of eye contact, immediately rinse with water for at least 15 minutes. Consult with a doctor. For respiratory problems, transport victim to fresh air. Remove contaminated clothes and clean before reuse.

WARRANTY STATEMENT

APN Specialty Coatings Inc. warrants that products delivered to purchasers are manufactured free from material defects and workmanship flaws in accordance with APN Specialty Coatings Inc. published specifications, provided installation follows APN Specialty Coatings Inc. recommended procedures. APN Specialty Coatings Inc. disclaims liability for any damages arising from improper product usage that deviates from its intended purpose or fails to comply with APN Specialty Coatings Inc. installation standards. APN Specialty Coatings Inc. assumes no liability regarding product installation and processing methods. This technical data information serves as general reference material only. Prior to any installation work, please reach out to your regional PurEpoxy Representative or contact our Technical Service team for professional guidance.